

REVERSION STATEMENT



The range of PVC matting we manufacture is made with Plasticized PVC, which, as with all thermoplastics, is susceptible to slight size changes.

These size changes can be as a result of two main causes:

Memory Shrinkage

This occurs where stress within the mat as a result of the manufacturing extrusion process are slowly released, causing a reduction of size. In extreme situations this can be 2%. This property is often referred to in thermoplastics as "memory shrinkage" or "reversion" because the plastic is returning to its unstressed state. The factor which affects the speed of memory recovery to the greatest extent is temperature. Rolls of matting laid in warm areas will shrink back quicker.

Memory shrinkage is a once only process.

Installation Mishandling

Due to the elastic nature of Plasticized PVC, a roll of matting that's inadvertently stretched by pulling or dragging during installation, will slowly recover to its original length after installation. Extreme cases of mishandling can result in 4% stretch. As with "Memory Shrinkage" the recovery process is accelerated in warmer environments.

In the majority of matting installations this shrinkage is not noticeable and only becomes apparent when the matting is positioned within a finite area with fixed boundaries.

Please note that our entrance mats are less susceptible to shrinkage as these rolls of matting are annealed prior to despatch. This process accelerates any memory shrinkage in the rolls by heating the matting in an oven to 158°F for 12 hours.

Please contact us should you have any further queries on this matter:

Plastex Matting Inc.

120 55th St NE
Fort Payne, AL 35967
+1 256 845 7725

USA + UK manufactured
matting products:
plastexmatting.com

Date: July 1997